

FWGPP60-PEK83HM

Face Material

weight	thickness	material
45 ± 10%g/m ² ISO 536	0.06 ± 10%mm ISO 534	Glossy opalescent polypropylene film with special coating

Liner

80 ± 10%g/m ² ISO 536	0.8 ± 10%mm ISO 534	Single-color plastic-coated white PEK release paper
----------------------------------	---------------------	---

Adhesive

A general permanent rubber adhesive. HM is an adhesive with a high initial viscosity and ultimate viscosity. Excellent performance on many packaging materials. It can be used for non-direct contact labeling of products such as food, electronics and cosmetics.

Peel adhesion

Initial adhesion 10N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 16N/25mm FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 8N/25mm FTM 2 st.st
--	--	--

Temperature

Min. Appl. Temp. 8°C	Service Temp. -5°C+60°C (after 24hrs)
----------------------	---------------------------------------

Applications

The material has certain tear resistance and chemical corrosion resistance, and its product is widely used in industries such as washing, cosmetics, daily chemicals, food and electronic.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The white high-gloss polypropylene film with pearl luster effect, with a layer of coating on the surface, suitable for flexographic printing, letterpress printing, screen printing and thermal transfer printing and other printing methods, and has good expressiveness to ink. Product labels with more important properties such as water resistance, oil resistance and chemical resistance, and good cover performance. Sharp knives should be used in die-cutting, and at the same time avoid adhesive overflow due to excessive winding tension.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.